



Corporate & Technical

Rmax Operating, LLC
 13524 Welch Road
 Dallas, Texas 75244-5291

Phone: (972) 387-4500

Fax: (972) 387-4673

Email: rmax@rmax.com

Web: www.rmax.com

2013-02

Nominal Thickness	Thermal R-Value ¹					
	R-Matte Plus-3 and Thermasheath-3	TSP-3,TSX-8500 and TSX-8510	ECOMAXci	Thermarroof Plus-3	Durasheath-3	TSA-FA-3
0.5	3.2	---	---	---	3.0	---
0.625	4.0	---	---	---	3.8	---
0.75	5.0	5.0	---	---	4.5	---
1.0	6.0	6.0	6.5	6.0	6.0	6.0
1.1	6.7	6.7	7.2	6.7	6.6	6.6
1.2	7.4	7.4	7.9	7.4	7.2	7.2
1.25	7.8	7.8	8.3	7.8	7.5	7.5
1.3	8.2	8.2	8.6	8.2	7.8	7.8
1.4	8.9	8.9	9.3	8.9	8.4	8.4
1.5	9.6	9.6	10.0	9.6	9.0	9.0
1.6	10.3	10.3	10.6	10.3	9.6	9.6
1.7	11.0	11.0	11.2	11.0	10.2	10.2
1.75	11.4	11.4	11.6	11.4	10.6	10.6
1.8	11.7	11.7	11.9	11.7	10.9	10.9
1.9	12.4	12.4	12.5	12.4	11.5	11.5
2.0	13.1	13.1	13.1	13.1	12.1	12.1
2.1	13.8	13.8	13.8	13.8	12.7	12.7
2.2	14.5	14.5	14.5	14.5	13.4	13.4
2.25	14.9	14.9	14.9	14.9	13.7	13.7
2.3	15.3	15.3	15.3	15.3	14.0	14.0
2.4	16.0	16.0	16.0	16.0	14.7	14.7
2.5	16.7	16.7	16.7	16.7	15.3	15.3
2.6	17.4	17.4	17.4	17.4	15.9	15.9
2.7	18.1	18.1	18.1	18.1	16.6	16.6
2.75	18.5	18.5	18.5	18.5	16.9	16.9
2.8	18.9	18.9	18.9	18.9	17.2	17.2
2.9	19.6	19.6	19.6	19.6	17.9	17.9
3.0	20.3	20.3	20.3	20.3	18.5	18.5
3.1	21.0	21.0	---	21.0	19.1	19.1
3.2	21.7	21.7	---	21.7	19.8	19.8
3.25	22.1	22.1	---	22.1	20.1	20.1
3.3	22.5	22.5	---	22.5	20.4	20.4
3.4	23.2	23.2	---	23.2	21.1	21.1
3.5	23.9	23.9	---	23.9	21.7	21.7
3.6	24.6	24.6	---	24.6	22.4	22.4
3.7	25.3	25.3	---	25.3	23.0	23.0
3.75	25.7	25.7	---	25.7	23.4	23.4
3.8	26.0	26.0	---	26.0	23.7	23.7
3.9	26.7	26.7	---	26.7	24.3	24.3
4.0	27.4	27.4	---	27.4	25.0	25.0
4.1	28.1	28.1	---	28.1	25.7	25.7
4.2	28.8	28.8	---	28.8	26.3	26.3
4.25	29.2	29.2	---	29.2	26.7	26.7
4.3	29.6	29.6	---	29.6	27.0	27.0
4.4	30.3	30.3	---	30.3	27.6	27.6
4.5	31.0	31.0	---	31.0	28.3	28.3

¹ Determined by using ASTM C518 test method at 75°F mean temperature on material conditioned according to PIMA Technical Bulletin No. 101.